



FUTUR-FLOOR EPOX A

TWO-COMPONENT WATER-BASED EPOXY COATING, PIGMENTED

Pigmented two-component epoxy coating in aqueous dispersion suitable for wet substrates with a satin-glossy finish for interior floors.

PROPERTIES

Quick and easy application.

Consumption of product appropriate for the required use.

Good adhesion to concrete with high mechanical resistance, resistance to abrasion and chemical agents.

Solvent-free, odor-free, suitable for indoor applications.

Possibility of non-slip finish.

PHYSICAL-CHEMICAL CHARACTERISTICS

Appearance*:	Liquid
Presentation:	Metal containers Component B, pigmented according to RAL chart
	4 Kg containers
	Component A: 172 Kg Component B: 2.28 Kg
	10 Kg containers:
	Component A: 43 Kg Component B: 5.7 Kg
Mixing ratio:	Component A: 57 parts. Component B: 43 parts weight
Chemical nature:	Water-based epoxy
Density at 20 °C*:	1,200 ± 0.050 Kg/L (20 °C, ASTM D1475)
Solid content:	70%
Viscosity:	500 MPa
Pot Life:	1 hour (25 °C)
Touch dry:	3-5 hours
Repainted:	48 hours
Total curing:	7 days
Support temperature:	> +10 °C, < +35 °C
Ambient temperature:	> +10 °C, < +35 °C
Relative humidity:	< 75%
Support humidity:	Accepts humidity
Wear resistance:	85 µm (UNE-EN 13892-4)
Adhesion strength:	> 3 N/mm ² (Pull-out test, UNE-EN 13892-8)
EN-13813 data:	
Fire behavior:	Bfl S1
Emission of corrosive substances:	SR



Water vapor permeability:	NPD
Wear resistance:	AR1
Adhesion:	B2.0
Shore D hardness:	NPD
Acoustic insulation:	NPD
Impact resistance:< /td>	>= IR4
Chemical resistance:	NPD

* Quality specifications. * Especificaciones de calidad.

MODE OF USE

Before applying the product, check that the support is clean and free of traces of oil, grease, silicone, contaminating waxes or soil materials. If repair is needed, apply appropriate repair mortars.

Apply at room temperature between +8 °C and 40 °C. The temperature of the support must be between +8 °C and 40 °C. The support must be dry and with relative humidity It is important to control the dew point to prevent condensation from occurring and avoid whitish areas on the coating.

It is necessary to start from a porous concrete support, without grout and free of curing liquids. Minimum compressive strength of concrete: 15 N/mm². Minimum tensile strength of concrete: 1 N/mm².

If in doubt, carry out a test before application.

Mix the two components in the recommended proportion of 4 parts by weight of component A for every 1 part by weight of component B. Beat component A well in its container, then add component B and beat with an electric stirrer (300-400 rpm) for a minimum of 1 minute until a homogeneous product is achieved. If overmixed, occluded air bubbles may appear. Once the two components are mixed, it is ready for use. The open application time (Pot Life) is 1 hour at 25 °C and 55% RH.

Before applying the product to the work surface, prepare a primer by diluting the product 10% with water. Spread the mixture well over the entire surface.

Apply with a brush, roller or airless spray in thin layers with an approximate consumption of 200-300 g/m². The final consumption will depend on the porosity and roughness of the support.

Repainting will be carried out once the previous layers have dried, approximately 12 hours. Do not repaint after 48 hours.

Touch dry: 3-5 hours

Pedestrian traffic: 24 hours

Light traffic: 2 days

Total curing: 7 days

Data at ambient temperature of +25 °C and 55% relative humidity.

For non-slip finishes, corundum must be added to the product in a proportion of 0.1-0.4 Kg/m². For non-abrasive anti-slip, add anti-slip in the same proportion.

Maintenance and cleaning: To maintain the appearance of the floor after application, all spills must be removed immediately after they have occurred. The floor must be cleaned regularly using rotating brushes, high-pressure cleaners, vacuum cleaners, using neutral detergents and appropriate waxes.

Once the container is opened, we recommend its complete consumption. Once the two components have been mixed, the mixture obtained must be applied, respecting the pot-life.

Stable for 12 months from its manufacturing date, in its original, well-closed and undamaged container. Store in a dry and cool place at temperatures between +5°C and +25°C.

Application in closed areas must be carried out ensuring proper ventilation during application and 48 hours after.

Do not exceed the maximum consumption because it may affect its adhesion and durability.

Avoid the formation of puddles of the product.

In applications exposed to U.V. rays. yellowing may occur.

For applications with chemical resistance, consult the technical department.



Incorrect treatment of cracks and singular points can lead to a reduction in the useful life of the pavement. To clean materials and utensils, use water before the product hardens. Once the product has hardened it can only be removed by mechanical means.

APPLICATIONS

Very useful in all types of construction companies, quick repair contracts, general masonry, community maintenance, building repair and restoration, high-resistance epoxy industrial flooring, etc.

Application as:

Treatment, decoration and protection of pavements, floors and rehabilitation of: Industrial floors, food floors, chemical resistance floors, floors resistant to vehicle traffic (light traffic), industrial warehouses and warehouses, etc.

Dust and anti-wear protection of concrete.

Finishing on multi-layer epoxy, self-leveling and polyurethane floors.

The information and recommendations we provide are based on our Research and experience and we believe they are correct. Since the application of the products by our Clients is beyond our control, we cannot assume responsibilities arising from misuse of our products.